

2008

Mass (%)	Cum %		Jan	Mesh	Size		Mass (%)	Cum %	
	Passing	Passing			Microns	mm		Passing	Passing
.212	8.19	91.81		+65	212	0.212	7.22	92.78	
.147	8.92	82.89		+100	147	0.147	9.66	83.12	
.104	12.81	70.08		+150	104	0.104	11.28	71.84	
.074	10.74	59.35		+200	74	0.074	8.35	63.49	
.037	17.12	42.23		+400	37	0.037	17.96	45.53	
0	42.23	0.00		-400	0	0	45.53	0.00	

Mass (%)	Cum %		Feb	Mesh	Size		Mass (%)	Cum %	
	Passing	Passing			Microns	mm		Passing	Passing
.212	7.95	92.05		+65	212	0.212	6.78	93.22	
.147	9.38	82.67		+100	147	0.147	9.47	83.75	
.104	13.11	69.56		+150	104	0.104	11.59	72.17	
.074	10.72	58.84		+200	74	0.074	9.12	63.04	
.037	16.57	42.26		+270	53	0.053	10.02	53.02	
0	42.26	0.00		+400	37	0.037	8.11	44.91	
				+500	25	0.025	5.96	38.95	
				-500	0	0	38.95	0.00	

Mass (%)	Cum %		Mar	Mesh	Size		Mass (%)	Cum %	
	Passing	Passing			Microns	mm		Passing	Passing
.212	8.99	91.01		+65	212	0.212	0.00	100.00	
.147	9.56	81.45		+100	147	0.147	0.00	100.00	
.104	13.01	68.44		+150	104	0.104	0.00	100.00	
.074	9.86	58.58		+200	74	0.074	42.05	57.95	
.037	15.99	42.59		+400	37	0.037	16.93	41.02	
0	42.59	0.00		-400	0	0	41.02	0.00	

Mass (%)	Cum %		Apr	Mesh	Size		Mass (%)	Cum %	
	Passing	Passing			Microns	mm		Passing	Passing
.212	7.79	92.21		+65	212	0.212	0	100.00	
.147	9.25	82.96		+100	147	0.147	0	100.00	
.104	12.41	70.55		+150	104	0.104	0	100.00	
.074	10.07	60.49		+200	74	0.074	40.79	59.21	
.037	15.94	44.54		+400	37	0.037	16.97	42.24	
0	44.54	0.00		-400	0	0	42.24	0.00	

	Mass (%)	Cum % Passing
.212	8.53	91.47
.147	9.23	82.24
.104	12.51	69.73
.074	9.95	59.78
.037	15.41	44.37
0	44.37	0.00

	Mass (%)	Cum % Passing
.212	7.42	92.58
.147	8.32	84.26
.104	11.66	72.60
.074	9.85	62.75
.037	16.24	46.51
0	46.51	0.00

	Mass (%)	Cum % Passing
.212	9.46	90.54
.147	8.37	82.17
.104	11.20	70.97
.074	9.42	61.54
.037	14.77	46.78
0	46.78	0.00

	Mass (%)	Cum % Passing
.212	12.38	87.62
.147	9.65	77.97
.104	11.77	66.21
.074	9.26	56.94
.037	14.77	42.17
0	42.17	0.00

	Mass (%)	Cum % Passing
.212	14.91	85.09

.147	10.70	74.40
.104	11.99	62.41
.074	9.28	53.13
.037	13.91	39.22
0	39.22	0.00

Cum %
Mass (%) Passing

.212	13.60	86.40
.147	10.43	75.97
.104	12.18	63.79
.074	9.38	54.42
.037	14.40	40.01
0	40.01	0.00

Cum %
Mass (%) Passing


.212	8.73	91.27
.147	9.54	81.73
.104	12.20	69.53
.074	9.87	59.65
.037	16.19	43.47
0	43.47	0.00

Cum %
Mass (%) Passing

.212	7.04	92.96
.147	8.99	83.96
.104	11.20	72.76
.074	8.70	64.06
.037	17.77	46.29
0	46.29	0.00

Materials


e	SILT SIZES	CLAY SIZES



Size (mm)

Materials

SILT SIZES



0.1

0.01

Size (mm)

CLAY SIZES

0.01

Granular Materials

